MS-478 SELF-ADHESIVE PIPE MARKERS AND LABELS W/ UV OVERLAMINATE

Technical Data



FUEL OIL RETURN

Description

MS-478 UV self-adhesive pipe markers and labels are manufactured from premium grade polyester with a permanent pressure-sensitive acrylic adhesive. They are used to provide line service designations, system color-coding or various labeling needs. Flow directional arrow tape or individual arrow markers are used with pipe markers to indicate direction of flow. MS-478 markers are available in a variety of standard and custom colors.

Physical and Chemical Characteristics

Base Material:	Premium-grade Polyester w/ UV Overlaminate		
Material Thickness:	.003" (.076 mm)		
Service Temperature:	-50°F to 250°F (-45°C to 121°C)		
Application Temperature:	+32°F (0°C)		
Chemical Resistance:	Excellent		
Water Resistance:	Excellent		
Expected Outdoor Durability:	Excellent (5+ Years)		
Storage Durability:	Up to 2 Years		
Abrasion Resistance:	Very Good		
Mounting:	Permanent pressure sensitive acrylic adhesive backing		
Finish:	Gloss Surface		
Text Height:	Designed to meet ANSI & ASME Standards (See chart)		
Typical Sizes:	Designed to meet ANSI & ASME Standards (See chart)		
Standard Colors:	Designed to meet ANSI & ASME Standards (See chart)		
Options:	Custom Sizes Available		
	Acid Resistance: Good		
Chemical Table:	Alkalis Resistance: Good		
Chemical Table.	Salts Resistance: Good		

Label Sizes and Letter Heights

Marker Size	Pipe Diameter (Including insulation)	Marker Style	Color Field	Letter Height
1" x 8"	3/4" – 2-1/4"	Α	8" long	3/4"
2-1/4" x 13"	2-1/2" – 7-7/8"	В	13" long	1-3/4"
4" x 24"	8" – 10"	С	24" long	2-1/2"
4" x 32"	Over 10"	D	32" long	3-1/2"

^{*}Individual arrow markers are the same width and one-half the length of the pipe markers

8265 N. Faulkner Road, Milwaukee, WI 53224

Ph: 800.234.0135 | Email: sales@markserv.com | Website: www.markserv.com

MS-478 SELF-ADHESIVE PIPE MARKERS AND LABELS W/ UV OVERLAMINATE

Technical Data

Designation of Colors (ASME A13.1-2023 & ANSI Z535-2017)

Designation of Colors — ASME A13.1-2023 & ANSI Z535-2017 Standards					
Classification	Color Scheme				
Defined Applications					
Firefighting	White text on red	Sample			
Toxic or corrosive	Black text on orange	Sample			
Flammable, combustible, or oxidizing	Black text on yellow	Sample			
Steam; or steam condensate, boiler feedwater, or other hot water	Black text on gray	Sample			
Potable, cooling, or other cold or tepid water	White text on green	Sample			
Compressed air	White text on blue	Sample			
Undefined Applications					
Defined by user	White text on purple	Sample			
Defined by user	Black text on white	Sample			
Defined by user	White text on brown	Sample			
Defined by user	White text on black	Sample			

Designation of Colors (ANSI/ASME A13.1-1996)

Designation of Colors — ANSI/ASME A13.1-1996 Standards					
Classification	Color Scheme				
Materials Inherently Hazardous					
Flammable or Explosive, Chemically Active or Toxic, Extreme Temperature or Pressures, Radioactive	Black text on yellow	Sample			
Materials Inherently Low Hazard					
Liquid or Liquid Admixture (non-hazardous materials)	White text on green	Sample			
Gas or Gaseous Admixture (non-hazardous materials)	White text on blue	Sample			
Fire Quenching Materials					
Water, Foam, CO2, Halon, etc.	White text on red	Sample			

Information on physical and chemical characteristics is based on tests we believe to be reliable. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material for their specific application.

Updated on 1/12/2024